GENERAL BUILDING PRODUCT DATA SHEET



# General Product Information

ROCKWOOL stone wool products are made of basalt, a volcanic stone.

ROCKWOOL stone wool products are non-combustible with a melting point of approximately 1000°C. They are particularly suitable for thermal insulation, fire protection and sound reduction / absorption.

ROCKWOOL stone wool is inorganic and contains

no nutritious substance. Therefore it will not be attacked by microorganisms. Mineral wool will not rot and does not attract vermin.

No CFCs, HFCs, HCFCs, or asbestos are used in the manufacture of ROCKWOOL stone wool products.

**CREATE AND PROTECT** 

**GENERAL BUILDING** PRODUCT DATA SHEET

## ThermalRock B (Blanket)

## Common applications

ThermalRock B is manufactured in a wide variety of thicknesses and densities to suit most requirements, suitable for general application in residential, commercial and industrial buildings.

#### **Dimensions**

Product	type Thickness (m	m) Length x Width (mm)
B40	50	5000 X 1200
	50	7500 X 1200
B50	50	5000 X 1200
	50	7500 X 1200
B60	25	10000 X 1200
	50	5000 X 1200
	50	7500 X 1200
B80	25	8000 X 1200
	25	10000 X 1200
	50	5000 X 1200
	50	7500 X 1200
B100	25	5000 X 1200
	25	8000 X 1200
	50	2500 X 1200
	50	4000 X 1200

Note: Please contact your local representatives for the specific densities and thicknesses that are available locally.

### **Facings**

ThermalRock B products are available in plain, aluminium foil facings and one-sided or two-sided glass tissue facings.

### Packaging and Storage

ThermalRock B is supplied in folded or roll form (depending on factory) and shrink-wrapped in polyethylene sheets for ease of handling, transportation, storage and identification. Products should be stored indoors or under a waterproof covering.



#### **Technical Parameters**

Product types	B40	B50	B60	B80	B100	Standards	
Nominal density (kg/m³)	40	50	60	80	100	ASTM C177/C518	
Thermal conductivity 20°C $\lambda$ values (W/mK)	0.037	0.036	0.036	0.036	0.036	BS 476 Part 4/EN 13501-1	
Sound absorption (BS EN 20354: 1993)	Please contact your local representative for more information						
Fire performance	Non-combustible (without facing)			ASTM C1104/C1104M			
Water vapour absorption	Absorb Less than 0.04%				EN 1609:97		
Water absorption (partial immersion)	Less th	an 1kg/m²					

Note: The information contained in this data sheet is believed to be correct at the date of publication. Rockwool Asia does not accept it consequences of using ThermalRock B in applications different from those described above.





20 Fortune Avenue, corner Santan Street, Brgy. Fortune, Marikina City, 1809 PH

Phone: +63(2) 8790-1000

#### **DAVAO OFFICE**

Unit 01-02 Tristar Warehouse, KM 11 Brgy. Communal Diversion Rd., Davao City, 8000 PH Phone: +63 (82) 234-0911 to 14

Email: info@worldhomedepot.com Email: info.davao@worldhomedepot.com